



# PVC SCHEDULE 80 FITTINGS

80-2-0199

## Performance Engineered & Tested



SPEARS Schedule 80 PVC fitting designs combine years of proven experience with computer generated stress analysis to yield the optimum physical structure and performance for each fitting. Material reinforcement is uniformly placed in stress concentration areas for substantially improved pressure handling capability. Resulting products are subjected to numerous verification tests to assure obtaining the very best PVC fittings available.

### Full 1/4" Through 12" Availability

Spears comprehensive line of injection molded PVC fittings offers a variety of configurations in molded Schedule 80 sizes 1/4" through 12" conforming to ASTM D 2467 and Spears exclusive CL150 Flanges in sizes 1/2" through 16".

### Exceptional Chemical & Corrosion Resistance

Unlike metal, PVC fittings never rust, scale, or pit, and will provide many years of maintenance-free service and extended system life.

### High Temperature Ratings

PVC thermoplastic can handle fluids at service temperatures up to 140°F (60°C), allowing a wide range of process applications, including corrosive liquids.

### Lower Installation Costs

Substantially lower material costs than steel alloys or lined steel, combined with lighter weight and ease of installation, can reduce installation costs by as

much as 60% over conventional metal systems.

### Higher Flow Capacity

Smooth interior walls result in lower pressure loss and higher volume than conventional metal fittings.

### Additional Fabricated Configurations through 36"

Extra large, hard-to-find, and custom configurations are fabricated from NSF Certified pipe. Fittings are engineered and tested to provide full pressure handling capabilities according to Spears specifications.

### Advanced Design Specialty Fittings

Spears wide range of innovative, improved products include numerous metal-to-plastic transition fittings and unions with Spears' patented stainless steel reinforced (SR) plastic threads.

### PVC Valves

SPEARS PVC Valve products are available for total system compatibility and uniformity; see SPEARS' THERMOPLASTIC VALVES PRODUCT GUIDE & ENGINEERING SPECIFICATIONS (V-4).



Quality Systems Certificate No. 293  
Corporate Facilities, Sylmar, CA  
Assessed to ISO 9001

### Sample Engineering Specifications

All PVC Schedule 80 fittings shall be produced by Spears Manufacturing Company from PVC Type I, cell classification 12454, conforming to ASTM Standard D 1784. All injection molded PVC Schedule 80 fittings shall be Certified for potable water service by NSF International and manufactured in strict compliance to ASTM D 2467. All fabricated fittings shall be produced in accordance with Spears General Specifications for Fabricated Fittings. All PVC flanges shall be designed and manufactured to meet CL150 bolt pattern per ANSI Standard B16.5 and rated for a maximum internal pressure of 150 psi, non-shock at 73°F.

**PROGRESSIVE PRODUCTS FROM SPEARS INNOVATION & TECHNOLOGY**

## PVC Thermoplastic Pipe Temperature Pressure De-Rating

System Operating Temperature °F (°C)	73 (23)	80 (27)	90 (32)	100 (38)	110 (43)	120 (49)	130 (54)	140 (60)
PVC	100%	90%	75%	62%	50%	40%	30%	22%

**NOTE: Valves, Unions and Specialty Products have different elevated temperature ratings than pipe.**

### PVC Basic Physical Properties

Properties	ASTM Test Method	PVC
<b>Mechanical Properties, 73°F</b>		
Specific Gravity, g/cm	D 792	1.40
Tensile Strength, psi	D 638	7,000
Modulus of Elasticity, psi	D 638	440,000
Compressive Strength, psi	D 695	9,000
Flexural Strength, psi	D 790	13,200
Izod Impact, notched, ft-lb/in	D 256	.65
<b>Thermal Properties</b>		
Heat Deflection Temperature, °F at 66 psi	D 648	165
Thermal Conductivity, BTU/hr/sq ft/°F/in	C 177	1.2
Coefficient of Linear Expansion, in/in/°F	D 696	3.0 x 10 <sup>-5</sup>
<b>Flammability</b>		
Limiting Oxygen Index, %	D 2863	43
UL 94 Rating	94V-0	
<b>Other Properties</b>		
Water Absorption, % 24 hr.	D 570	.05
Industry Standard Color	White / Gray	
ASTM Cell Classification	D 1784	12454
NSF Potable Water Approved	Yes	

### PVC Chemical Resistance

PVC is generally inert to most mineral acids, bases, salts and paraffinic hydrocarbon solutions. For more information on PVC chemical resistance refer to the Chemical Resistance of Rigid Geon® Vinyls Based on Immersion Test, published by the GEON® company.

### NOT FOR USE WITH COMPRESSED AIR OR GASES

Spears Manufacturing Company DOES NOT RECOMMEND the use of thermoplastic piping products for systems to transport or store compressed air or gases, or the testing of thermoplastic piping systems with compressed air or gases in above and below ground locations. The use of our product in compressed air or gas systems automatically voids any warranty for such products, and its use against our recommendation is entirely the responsibility and liability of the installer.

**WARNING: DO NOT USE COMPRESSED AIR OR GAS TO TEST ANY PVC OR CPVC THERMOPLASTIC PIPING PRODUCT OR SYSTEM, AND DO NOT USE DEVICES PROPELLED BY COMPRESSED AIR OR GAS TO CLEAR SYSTEMS. THESE PRACTICES MAY RESULT IN EXPLOSIVE FRAGMENTATION OF SYSTEM PIPING COMPONENTS CAUSING SERIOUS OR FATAL BODILY INJURY.**



## SPEARS® MANUFACTURING COMPANY

### CORPORATE OFFICES

15853 Olden Street, Sylmar, CA 91342  
P.O. Box 9203, Sylmar, CA 91392  
(818) 364-1611 • <http://www.spearsmfg.com>



#### PACIFIC SOUTHWEST

15860 Olden Street  
Sylmar (Los Angeles), CA 91342  
P.O. Box 9203, Sylmar, CA 91392  
(818) 364-1611  
(800) 862-1499  
FAX: (818) 367-3014

#### NORTHWEST

3902 "B" Street N.W.  
Auburn (Seattle), WA  
98002  
(253) 939-4433  
(800) 347-7327  
FAX: (253) 939-7557

#### ROCKY MOUNTAIN

4800 Nome Street  
Denver, CO  
80239  
(303) 371-9430  
(800) 777-4154  
FAX: (303) 375-9546

#### SOUTH CENTRAL

1838 Forms Drive  
Carrollton (Dallas), TX  
75006  
(972) 245-0387  
(800) 441-1437  
FAX: (972) 245-4205

#### UTAH

1415 South 700 West #3  
Salt Lake City, UT  
84104  
(801) 972-0659  
FAX: (801) 972-0688

#### NORTHEAST

543 Industrial Drive  
Lewisberry (Harrisburg), PA  
17339-9532  
(717) 938-8844  
(800) 233-0275  
FAX: (717) 938-6547

#### SOUTHEAST

2751 Miller Road  
Decatur (Atlanta), GA  
30035  
(770) 981-7122  
(800) 662-6326  
FAX: (770) 981-6106

#### FLORIDA

3445 Bartlett Boulevard  
Orlando, FL  
32811  
(407) 843-1960  
(800) 327-6390  
FAX: (407) 425-3563

#### MIDWEST

854 Fairway Drive  
Bensenville (Chicago), IL  
60106  
(630) 773-0075  
(800) 662-6330  
FAX: (630) 773-0435

#### INTERNATIONAL SALES

15853 Olden Street  
Sylmar (Los Angeles), CA 91342  
P.O. Box 9203  
Sylmar, CA 91392  
(818) 364-1611  
FAX: (818) 898-3774  
E-mail: [export@spearsmfg.com](mailto:export@spearsmfg.com)